



Arrotile Platinum

(Grey/White)

Super Flex Multipurpose Floor
and Wall Tile and Stone Adhesive

CLASS:

C2TES1

IS 15477:2019



TYPE 3 TS1



Features / Benefits

- Signal Component, Just add Water.
- Easy to use & Economical
- High strength with various Substrate.
- Water & Shock Resistance
- Complies with IS 15477:2019 - Type3 T S1 Adhesive Standards.
- High Open Time
- High Adjustability time

Complies

- IS 15477 : 2019 Type 3 T S1 Adhesive
- EN 12004 / ISO 13007 : C2TES1 ADHESIVE
- ANSI : A 118.4 ET

Working Properties (21° C)

Arrotile Platinum High Polymer Adhesive
Mixed With Water.

Open Time	30 Minutes
Adjustability Time	30 Minutes
Pot Life	4 Hours
Time to Heavy Traffic	24 Hours

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

Suitable Substrate

- Cement Mortar Beds
- Cement Plaster
- Brick Masonry Surface
- Concrete Surfaces
- Cement Terrazzo
- Quarry, Cement Body Tiles
- Slim Porcelain large formate tiles
- Cement & Concrete Masonry
- Trimix / VDF Concrete
- Ceramic Tile, Vitrified Tile and Natural Stone
- Cement Backer Board***

Application

Design Especially for Interior and Exterior Floor and Wall Installations of all types of ceramic tile vitreous/vitrified, semi-vitreous tile, glass mosaic tiles, precast terrazzo, and natural stones over concrete and on a variety of substrates. Good underwater shear bond allows this product to be used for wet areas like swimming pools, sauna, water bodies and washrooms. Can also be used as slurry bond adhesive in wet on wet application tile on tile application.



Performance Properties:

ARROTILE PLATINUM High Polymer Adhesive mixed with Water

Applicable Standards:

IS15477:2019 / ANSI A118.4; EN 12004 & ISO 13007;

ANSI Data		
Property : Test method	Requirement	Typical Values
Open Time (25 Minutes at 28 days): ANSI A118.4 Clause – 5.3	≥ 75 psi (0.50 Mpa)	120 psi – 140 psi (0.82 – 0.96 Mpa)
Sag: ANSI A118.4- Clause 6.0	≤ 0.02 Inches (0.50 mm)	0.012 – 0.016 Inches(0.30-0.40 mm)
Glazed wall tile Shear Strength		
7 Days: ANSI A118.4 – Clause 7.1.2	>3 00psi (2.07 Mpa)	325-350 psi (2.23 Mpa -2.40 Mpa)
7 Days Water immersion: ANSI A118.4- Clause 7.1.3)	>20 Opsi (1.38Mpa)	225-250 psi (1.54 Mpa-1.72 Mpa)
Porcelain Mosaic Tile Shear Strength		
1 Day: ANSI A118.4 – Clause 7.2.2	>75 psi (0.50 Mpa)	125 - 175 psi (0.86 – 1.20 Mpa)
7 Days: ANSI A118.4 – Clause 7.2.3	>200 psi (1.38Mpa)	250 - 275 psi (1.72 – 1.89 Mpa)
7 Days Water immersion: ANSI A118.4 – Clause 7.2.4	>150 psi (1.03 Mpa)	200 - 250 psi (1.37 – 1.72 Mpa)
28 Days: ANSI A118.4 – Clause 7.2.5	>200 psi (1.38Mpa)	250 - 300 psi (1.72 – 2.06 Mpa)
28 Days : Freeze Thaw cycling. ANSI A118.4 – Clause 7.2.5	>175psi (1.20Mpa)	225 - 275 psi (1.54 – 1.89 Mpa)
12 Weeks: ANSI A118.4 – Clause 7.2.7	>200psi (1.38Mpa)	250 - 300 psi (1.72 – 2.06 Mpa)
Quarry Tile Shear Strength		
28 Days : ANSI A118.4 – Clause 7.3.2	>150psi (1.03Mpa)	200 - 250 psi (1.37 – 1.72 Mpa)
28 Days :Freeze- Thaw cycling. ANSI A118.4 – Clause 7.3.3	>100psi (0.69Mpa)	150 - 200 psi (1.03 – 1.37 Mpa)

The adhesive mortar conforms to ANSI A118.4ET

EN / ISO Data		
Property: Test Method	Requirement	Typical Values
Open Time: EN 1346	≥ 0.50 N/mm ²	0.75 – 1.00 N/mm ²
Slip Resistance: EN 1308	≤ 0.50 mm	0.25 - 0.35 mm
Tensile Adhesion Strength		
Initial: EN 1348 – Clause 8.2	≥ 1.00 N/mm ²	1.25 – 1.50 N/mm ²
After Water Immersion : EN 1348 – Clause 8.3	≥ 1.00 N/mm ²	1.25 – 1.50 N/mm ²
Heat Ageing: EN 1348 – Clause 8.4	≥ 1.00 N/mm ²	1.00 – 1.25 N/mm ²
Freeze Thaw: EN 1348 – Clause 8.5	≥ 1.00 N/mm ²	1.25 – 1.50 N/mm ²

The adhesive mortar conforms to EN12004 / ISO 13007 as C2 TE S1

IS Data		
Property : Test method	Requirement	Typical Values
Tensile Adhesion		
Dry Condition – Annex A (Clause 5.1)	Minimum 1.5 N/mm ²	1.55-1.65 N/mm ²
Dry Condition – Annex A (Clause 5.1)	Minimum 1.0 N/mm ²	1.10-1.20 N/mm ²
Shear Adhesion		
Dry Condition – Annex B (Clause 5.2)	Minimum 1.5 N/mm ²	1.60-1.70 N/mm ²
Heat Ageing – Annex B (Clause 5.2)	Minimum 1.0 N/mm ²	1.10-1.20 N/mm ²
Wet Conditions – Annex B (Clause 5.2)	Minimum 1.0 N/mm ²	1.15-1.25 N/mm ²
Slip Resistance		
Slip Resistance- Annex E (Clause 5.5)	≤0.5 mm	0.35-0.45 mm

The Adhesive mortar conforms to IS 15477: 2019 - Type 3T S1 Adhesive

Packaging:

20 & 40 kg BOPP bags

Colour:

Grey and white

Coverage :

Approx. 55-60 Sft per 20 kg pack using 6mm x 6mm square notched trowel for a bed of 3mm.

Coverage will vary depending on trowel notch size, type and size of tile and substrate smoothness and evenness

Installation

Surface Preparation:

All surfaces should be between 40° F(4°C) and 104° F(40°C) and structurally sound, clean and free of all dirt, oil, grease, loose peeling paint, laitance, concrete sealers or curing compounds.

Check the surface to be true to plumb. All slabs must be plumb and true to within $\frac{1}{4}$ " (6mm) in 10 ft(3m). Rough or uneven concrete surfaces should be made smooth with Screed/Plaster material to provide a wood float (or better) finish.

Dry, dusty concrete slabs or masonry should be dampened and excess water swept off. Installation may be made on a damp surface. New concrete slabs shall be damp cured and 28* days old before application.

*No minimum cure time for concrete slabs when thin-set mortar is mixed with latex additive.

Expansion joints shall be provided through the tile work from all construction or expansion joints in the substrate. Do not cover expansion joints with thin set mortar. Follow ANSI Specification AN-3.8 "Requirements for Expansion Joints"

MIXING :

Place clean, potable water into a clean mixing bowl. Add ARROTILE PLATINUM High Flex powder into the mixing bowl. Use approximately 6.8 - 7.5L of water for 25 kg of powder. Mix by hand or with a slow speed mixer to a smooth, trowelable consistency. Allow adhesive to slake for 5 minutes. Adjust consistency if necessary. Remix and apply with the proper sized notched trowel.

NOTE :

Addition of ARROTILE PLOYMIX latex admix*, partially or completely replacing water would enhance the bond strength, flexibility of the thinset mortar.

* Contact ARROTILE technical services for large format tile or stone installations on exterior surfaces.

Application

a) TILE/STONE

Apply adhesive to the substrate with the flat side of the trowel, pressing firmly to work into surface. Comb on additional adhesive with the notched side. Use the proper sized notched trowel to ensure full bedding of the tile. Spread as much adhesive as can be covered with tile in 10 minutes. Back butter large format tiles (> 12"x12") to provide full bedding and firm support. Place tiles into wet, sticky adhesive and beat in using a beating block and rubber mallet to embed tile and adjust level. Check adhesive for complete coverage by periodically removing a tile and inspecting bedding adhesive transfer onto back of tile. Use of Arrotile spacers is recommended to provide grout joints between tiles / stones. The joint width shall be as per the recommendation of architect / engineer. Remove the spacers when the adhesive is set firm.

If adhesive is skinned over (not sticky), remove and replace with fresh adhesive.

b) GLASS MOSAIC TILES

The Arrotile Platinum High Flex adhesive shall be applied to the surface to be tiled with a notched trowel using a scraping motion to work the adhesive into good contact with the surface to be covered. Notch trowel with notches approximately 4mm is recommended to get a bed thickness of 1.5-2mm. V-notch of 3mm also can be used to get bed thickness of 1.5mm. Apply only so much that can be covered with tile within 10-15 minutes or while the adhesive surface is still tacky. The Glass Mosaic tiles shall then be set in place and beaten gently with mallet or grouting float to insure 100% full bedding. Tiles shall be aligned to achieve uniform joints and then allowed to set until firm. Excess adhesive must be cleaned from the surface of the tile with a wet cloth or sponge while the adhesive is fresh and has not hardened.

NOTE TO THE SPECIFIER AND INSTALLER:

After the tiles are set firm, the face of the sheets of front mounted glass mosaic tiles shall then be dampened and the face mount paper can be removed.

While installing tile/stone on the external walls and floors, we need to provide the joints by creating spaces between the tiles/stones and fill them up with Arrotile cement based grout mixed with Arrotile Ploymix (In the absence of spacer joints, the surface movements can push tiles/stones away from the substrate causing de-bonding of tiles or stones)

The exterior tile / stone installations are provided with joints (spaces) on the periphery of the area without allowing the tile / stone to be bound by the peripheral masonry work or plaster.

HOT & COLD WEATHER TILING:

* Please refer technical document on Hot & Cold weather tiling.

Grouting:

Grout installation shall be commenced after a minimum of 24 hours curing time at 70°F (21° C). Grout with Arrotile grout mixed with Arrotile polymix For maximum stain resistance of Internal spacer joints applications, use Arropoxy Tile grout Stainfree Grout.

For Feedback / Suggestion & Complaints:

Arrotile Constrochem Private Limited

Corporate Office: Rajkot-360 004.(Guj.) INDIA.

Unit - 1 : Khambha, Rajkot - 360 311. (GUJ.) India.

Unit - 2: Mouda, Nagpur - 441 001, (MH) India

Customer Care: +91 72 77 33 22 66

Email: arrotileconstrochem@gmail.com



Disclaimer :

The product information and the recommendations relating to the application and end-use of Arrotile products, are based on Arrotile current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Arrotile recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Arrotile reserves the right to change the properties of its products without notice, so the company does not assume liability of any legal from this product information.