



# Tetrabond SBR Latex

Mortar And Screed Modifier Cum Bonding Aid (45% Solid Content)



## Description

Tetrabond SBR Latex is based on modified styrene butadiene latex supplied as a ready to use bonding agent in liquid consistency. It is used for repair of spalled concrete – floors, columns, beams, chhajjas, slabs. Waterproofing of toilets & bathrooms, small terraces etc. It bonds strongly to old & new concrete and to plasters. It reduces shrinkage, prevents cracking, dust pick up & improves abrasion resistance

## Area of Application

- For concrete repairs - Spalled concrete of floors, columns, beams, chhajjas, slabs, parapets, etc.
- For waterproofing – Small roof terraces, sunken portions of toilets & bathrooms, chhajjas & lift pits, balconies & staircases.
- For waterproofing – Liquid & effluent tanks, car decks & walkways.
- As a bonding agent – Bonding mortar for tiles & panels, as undercoat for special finishes such as top rendering coat for chemical resistant floors.
- As a bond coat – For bonding of new concrete to old concrete, masonry stone work, plastering.
- For cladding – Fixing or re-fixing of slip bricks, tiles, stones & marble bedding.
- As external rendering – Weatherproof & frost resistant render, high wear & erosion resistant render. As bonding slurry coat for pinhole treatment on concrete surface & as repair mortar for overhead application.

## Features & Benefits

- Multipurpose – It is multipurpose & economical product, easy to use.
- Cracking – It prevents cracking by improving flexural strength.
- Hardness – Improves the hardness & prevents dust generation.
- Shrinkage – Reduces drying & aging shrinkage cracks.
- Bonding – Bond strongly to concrete, masonry, stonework, plasters, cementitious surfaces, asphalt & most of the building materials.
- Erosion & corrosion – Improves erosion resistance & prevents corrosion.
- Abrasion resistance – Improves abrasion resistance of the cement mix.
- Grouting – Reduces viscosity of cement injection grout for better fluidity & bonding

## Packaging

Available in 100, 500 gm, 1,3,5,10,20 kgs.packs.

## Dosage

10 litres Tetrabond SBR Latex per 50 kg OPC Cement



## Method of Application

### 1 SURFACE PREPARATION

- Clean the surface with wire brush or scrubber to remove hidden dirt, loose particles, laitance & dust. Degrease the surface by using suitable solvents.
- Repair the spalled concrete portion by saw, cutting the extreme edges of the repair location to a depth of at least 10 mm to avoid featheredging & to provide strong bond.
- Clean the concrete surface to remove any contamination where breaking is not possible. Roughen the surface by light scabbling or grit blasting.
- Expose corroded rebar in the repairing area fully. Remove all loose scales & corrosion deposits and immediately clean the surface.

### 2 PRIMING

- For priming of concrete substrate, the surface should be thoroughly saturated with potable water. Remove any excess of water prior to application. Slurry of primer coat is prepared by mixing of one part Tetrabond SBR, one part of water and 3 parts of fresh OPC cement. Slowly mix cement with binder to obtain a smooth consistency. Continue mixing the slurry during application to prevent settlement.

### 3 MIXING

- A Forced Action Mixer Is Essential (pan Mixer) & Recommended To Ensure That Tertabond SBR Mortar Is Thoroughly Mixed Or Use A Suitable Sized Drum With Heavy-duty Electrical Drill Machine Fitted With Spiral Paddle Mixer At Slow Speed Of 400-500 Rpm.
- Hand mixing is permissible only for 25 kg or less quantity.
- Charge the mixer with required quantity of clean & dry sand, cement & mix for 1-2 minutes, then add Tetracoat SBR Latex as per the dosages recommended. Mix for 2-3 minutes to avoid air entrapment. Keep on slowly adding water until the required consistency is achieved. Do not add extra water.

## Application

- Wide Range Of Mix Designs Are Recommended For Different Application Using Tetrabond SBR Latex

Sl No.	Application	Composition	Quantity of Dr. Fixit Pidicrete URP	Consistency & thickness
1	Patching & Repair Mortar & dry	<ul style="list-style-type: none"> <li>- OPC – 50 Kg</li> <li>- graded sharp &amp; washed &amp; dry sand – 150 Kg</li> <li>- water – 10 litres</li> </ul>	10 litres	Mortar consistency, 6-40 mm thickness
2	Heavy duty floor screed	<ul style="list-style-type: none"> <li>- OPC – 50 Kg</li> <li>- graded sharp &amp; washed sand – 75 Kg</li> <li>- granite chips (3-6 mm) – 75 Kg</li> <li>- water – 6 litres</li> </ul>	10 litres	Semi dry cohesive consistency, 10-40 mm thickness
3	Renders	<ul style="list-style-type: none"> <li>- OPC – 50 Kg</li> <li>- graded sharp &amp; washed sand – 150 Kg</li> <li>- water – 6 litres</li> </ul>	10 litres	Mortar consistency, 6-9 mm thickness
4	Bonding Mortar for slip bricks & tiles	<ul style="list-style-type: none"> <li>- OPC – 50 Kg</li> <li>- graded sharp &amp; washed sand – 125 Kg</li> <li>- water – 7 litres</li> </ul>	10 litres	Mortar consistency, 6-40 mm thickness.

## Health & Safety

- Do not add extra water or more than recommended dosage.
- Recommended dosage to be followed to achieve desired results.

## Technical Information

PROPERTIES	SPECIFICATION	RESULTS
Base		SBR latex (styrene, butadiene rubber)
Coverage oPCS: URP, 1:5 pbwt		20 – 22 sq ft/kg for two coats 1:1.5
total active solid content		45 ± 2%
pH		8 – 9
pot life @ 30 °C		30 – 45 minutes at 30 °C
Speciic gravity at 30 °C		1.01+/- 0.02
pH		7 to 9
Compressive strength, n/mm <sup>2</sup> – 7 days	( BS6319 part2:1983)	Passes the specification.
tensile strength,n/mm <sup>2</sup>	( aStM C – 190-85)	Passes the specification
flexural strength,n/mm <sup>2</sup>		9>
Slant shear bond, n/mm <sup>2</sup>	aStM 881	30
Chemical resiatance to mild acids, alkalies, sulphates.		Resists
Resistance to water pres - sure, bar		Upto 2
freeze thaw resistance		excellent

For Feedback / Suggestion & Complaints :

### Arrotile Constorchem Private Limited

Corporate Office : Rajkot-360 004.(Guj.) INDIA.

Unit - 1 : Khambha, Rajkot - 360 311. (GUJ.) India.

Unit - 2 : Mouda, Nagpur - 441 001, (MH) India

Customer Care : +91 72 77 33 22 66

Email : arrotileconstrochem@gmail.com



### Disclaimer :

The product information and the recommendations relating to the application and end-use of Arrotile products, are based on Arrotile current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Arrotile recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Arrotile reserves the right to change the properties of its products without notice, so the company does not assume liability of any legal from this product information.